

**FLEXURAL BEHAVIOR OF STEEL FIBER REINFORCED CONCRETE
BEAMS**

HAMID PESARAN BEHBAHANI

A project report submitted in partial fulfillment of the
requirements for the award of the degree of
Master of Engineering (Civil-Structure)

Faculty of Civil Engineering
Universiti Teknologi Malaysia

APRIL, 2010

ABSTARCT

Concrete is good in compression but weak in tension that is, concrete is a brittle material. So, in order to improve the tensile properties, short fibers are used. Effects of steel fibers on flexural performance of reinforced concrete (RC) beams are the main objectives of this study. The hooked-end steel fibers with the dimensions of 0.75 mm in diameter, 50 mm in length and with the aspect ratio of 67 were used in this study. Initially the optimum percentage addition of steel fibers in concrete was determined. In order to accomplish this task, several concrete prisms and cubes with the same mix proportioning of concrete and different volume fractions of steel fiber (0.5 %, 1%, 1.5 %, and 2 %) were prepared. Then, by determining the flexural and compressive strength of samples, it was concluded that the optimum volume fraction was 1 % ($78.5\text{kg}/\text{m}^3$). In the next step, the flexural behavior of RC beams with the addition of steel fibers with lower and higher compressive strength of concrete was considered. The study was conducted on two types of concrete with different grades of 30 and 50. For each grade of concrete, two beams were cast which steel fiber was included in one of the beams, with the addition of 1% volume fraction, and the other beam was considered as control beam. The overall dimensions of the beams were 170 mm in height, 120 mm in width, and 2400 mm in length. The beams were tested under four-point loading test. The results showed that addition of steel fibers in concrete increases the first cracking load, ultimate load, stiffness and ductility of the concrete beams. Furthermore, the addition of steel fibers has more effect on the properties of RC beams with higher concrete grade compared to lower grade.

ABSTRAK

Konkrit merupakan bahan yang kuat dalam mampatan tetapi lemah dalam tegangan iaitu ia adalah bahan yang rapuh. Oleh itu untuk meningkatkan sifat tegangan konkrit gentian pendek digunakan. Kesan gentian keluli terhadap prestasi lenturan rasuk konkrit bertetulang adalah objektif utama kajian ini. Gentian keluli yang mempunyai hujung bengkok berdiameter 0.75 mm, panjang 50 mm dan nisbah aspek bernilai 67 digunakan dalam kajian ini. Pada peringkat permulaan kadar optima penambahan gentian ditentukan. Bagi mencapai tujuan ini beberapa prisma dan kiub konkrit dengan kadar bahan campuran konkrit yang sama dan peratus gentian yang berbeza (0.5%, 1%, 1.5% dan 2%) telah disediakan. Hasil daripada penentuan kekuatan tegangan dan mampatan sampel telah diperolehi kadar optima gentian keluli ialah 1% (78.5kg/m^3). Seterusnya kelakuan lenturan rasuk konkrit bertetulang dengan penambahan gentian keluli menggunakan dua kekuatan konkrit yang rendah dan tinggi telah dibuat. Kajian dilakukan menggunakan dua gred konkrit berbeza iaitu gred 30 dan 50. Bagi setiap gred konkrit dua rasuk dibuat dengan satu rasuk ditambah 1% gentian keluli dan rasuk kawalan. Ukuran keseluruhan rasuk ialah 170 mm tinggi, 120 mm lebar, dan 2400 mm panjang. Rasuk telah diuji di bawah pembebanan empat titik. Keputusan menunjukkan penambahan gentian keluli meningkatkan beban retakan, beban maksimum, kekukuhan dan kemuluran rasuk konkrit. Selain daripada itu, penambahan gentian keluli mempunyai kesan yang lebih terhadap sifat-sifat rasuk konkrit yang bergred lebih tinggi berbanding konkrit gred rendah.

TABLE OF CONTENT

CHAPTER	TITLE	PAGE
	TITLE PAGE	i
	DECLARATION	ii
	ACKNOWLEDGEMENTS	iv
	ABSTRACT	v
	TABLE OF CONTENT	vii
	LIST OF TABLES	x
	LIST OF FIGURES	xi
1	INTRODUCTION	1
	1.1 Introduction	1
	1.2 Problem Statement	3
	1.3 Thesis Objectives	3
	1.4 Scope of study	3
	1.5 Structure of Thesis	4
2	LITERATURE REVIEW	5
	2.1 General	5
	2.2 Different Types of Fibers	6
	2.3 Steel Fiber Reinforced Concrete	8
	2.4 Disadvantage of Addition of Steel Fibers in to Concrete	11
	2.5 Application of Steel Fibre Reinforced Concrete	12
	2.6 Mechanical Properties of Steel Fibre Reinforced Concrete	13
	2.6.1 Compressive Strength	14

	2.6.2	Shear Strength	15
	2.6.3	Tensile Strength	16
	2.6.4	Impact Resistance	17
	2.6.5	Durability	17
	2.6.6	Flexural Strength and Toughness	19
		2.6.6.1 Effects of Steel Fibers on Flexural Behavior of RC Beams	22
		2.6.6.2 Effects of Aspect Ratio on Flexural Strength of Steel Fiber Reinforced Concrete	25
		2.6.6.3 Effects of Volume Fraction on Flexural Strength of Steel Fiber Reinforced Concrete	28
3		METHODOLOGY	30
	3.1	Introduction	30
	3.2	Determining Optimum Addition of Steel Fibers in Concrete	30
		3.2.1 Compressive Strength Test	31
		3.2.2 Flexural Strength Test	32
		3.2.3 Vebe Time Test	32
	3.3	Flexural Performance of SFRC Beams with Lower and Higher Compressive Strength of Concrete	33
		3.3.1 Four-Point Loading Test	34
		3.3.2 Steel Reinforcement Design and Preparation of Steel Bars	35
		3.3.3 Preparation of Formwork	36
	3.4	Materials	36
	3.5	Mix Proportioning	38
	3.6	Method for Mixing the Concrete	39
	3.7	Curing Method of Specimens	40

4	RESULTS AND DISCUSSIONS	41
4.1	General	41
4.2	Determining Optimum Addition of Steel Fibers in concrete	42
4.2.1	Compressive Strength Results	42
4.2.2	Flexural Strength Results	43
4.2.3	Workability	44
4.2.4	Discussions to Determine Optimum Addition of Steel Fibers	45
4.3	Flexural Performance of SFRC Beams with Lower and Higher Compressive Strength of Concrete	46
4.3.1	Ultimate Strength	46
4.3.2	Load-Deflection	46
4.3.3	Steel Strain	48
4.3.4	Mode of Failure	49
5	CONCLUSION AND RECOMMENDATIONS	51
5.1	Conclusion	51
5.2	Recommendations	52
	References	53

LIST OF TABLES

TABLE NO.	TITLE	PAGE
2.1	General Properties of Fibers[Johnson,Colin D., 1980]	8
2.2	Average Flexural Strength of Different Combinations of Concrete Measured on 150 x 150 x 750 mm Prisms (Fatih Altun <i>et al.</i> , 2005)	20
2.3	Results of the Bending Experiments on RC and SFARC beams (Fatih Altun <i>et al.</i> 2005)	24
2.4	Summary of Results-Concrete (1:2:3, 0.60) Specimen with 1.0 Percent by Volume of Reinforcement in Flexure	28
3.1	Summary of Testing Programs to Obtain Optimum Volume Fraction of Steel Fibers in SFRC	32
3.2	Summary of Testing Program to Study Flexural Performance of SFRC Beams	33
3.3	Properties of Cement	37
3.4	Specification of Steel Fibers which Used in This Study	38
3.5	Mix Proportioning of the Concrete Grades 30 and 50	39
4.1	Compressive Strength of Normal and Steel Fiber Added Concrete Cubes	42
4.2	Flexural Strength of SFRC and Normal Concrete Prisms	44
4.3	Vebe Time Test for Determining the Workability	44
4.4	Ultimate Load and First Crack Load of RC Beams	46
4.5	Ultimate Load and Deflection at Ultimate Load	48
4.6	Cracking Properties of the RC Beams	50

LIST OF FIGURES

FIGURE NO.	TITLE	PAGE
2.1	Fiber Classifications [James Patrick Maina Mwangi, 1985]	7
2.2	Different Shapes of Steel Fibers (ACI544.IR 1996)	9
2.3	Load-Deflection Curves for Plain and Fibrous Concrete (ACI 1996)	10
2.4	Effects of Steel Fibers Content on Compressive Stress-Strain Curve of FRC (Padmarajaiah and Ramaswamy 2002)	15
2.5	Influence of Fibre Content on Tensile Strength (Johnstone ACI-SP44-Detripit 1974)	16
2.6	Effect of Fibre Content on Concrete Electrical Resistivity (Chih-Ta Tsai <i>et al.</i> , 2008)	19
2.7	Effects of Volume of Fibres in Flexure (Shah <i>et al.</i> 1971)	21
2.8	Effects of Volume of Fibers in Tension and Toughness (US Army Corps of Engineers 1965)	22
2.9	Experimental Moment versus Deflection Curves for SFRC Beams (Craig 1984)	23
2.10	The Effect of w/d on the Flexural Strength of Mortar and Concrete (Johnston 1974)	25
2.11	The Effect of w/d on the Flexural Toughness of SFRC (Johnston 1974)	26
2.12	A Range of Load-Deflection Curves Obtained in the Testing of Steel Fibre Reinforced Concrete (Johnston 1982)	27
3.1	Cube Test Arrangement	31
3.2	Beam Test Schematic (all dimensions are in mm)	34
3.3	Four Point Loading Test	34
3.4	Cross Sections of RC Beams	35
3.5	Arrangement of Reinforcement Bars and Wooden Formwork	36

3.6	Strain Gauge Installation at the Center of Reinforcement Bars	36
3.7	Hooked End Shape Steel Fibers used in this Study	38
4.1	Compressive Strength Vs Age of Mixes with Different Percentage of Steel Fibers	43
4.2	Load versus Deflection Graph of the Beams	47
4.3	Load versus Steel Strain Curve	48
4.4	Mode of Failure of Lower Strength RC Beam after Failure	49
4.5	Mode of Failure of Higher Strength RC Beam after Failure	49
4.6	Mode of Failure of Lower Strength SFRC Beam after Failure	49
4.7	Mode of Failure of Higher Strength SFRC Beam after Failure	49

CHAPTER 1

INTRODUCTION

1.1 Introduction

Concrete is by far one of the most important building materials and its consumption is increasing in all countries and regions around the globe. The reasons are many such as: its components are available everywhere and relatively inexpensive, its production may be relatively simple, and its application covers large variety of building and civil infrastructure works. In addition, it has the lowest cost to strength ratio compared to other available materials.

One of the characteristics of the plain concrete is low tensile strength, and low tensile strain capacities; that is, concrete is a brittle material. Thus concrete require reinforcement before it can be used extensively as construction material. Historically this reinforcement has been in the form of continuous reinforcing bars which could be placed in the structure at the appropriate locations to withstand the imposed tensile and shear stresses. Fibers, on the other hand, are generally, short discontinuous, and are randomly distributed throughout the concrete to produce a

new construction material, known as Fiber Reinforced Concrete (FRC). Fibers used in cement-based materials are primarily made of steel, glass, and polymer or derived from natural materials. Since fibers tend to be more closely spaced than conventional reinforcing bars, they are better at controlling cracking. It is important to recognize that, in general, fiber reinforcement is not a substitute for conventional reinforcement. Fibers and steel bars have different roles to play in modern concrete technology, and there are many applications in which both fibers and continuous reinforcing bars should be used.

Initially, fibers are used to prevent and control plastic and drying shrinkage in the concrete. After some research and improvement, the addition of fibers material in the concrete can also improve the other concrete properties such as flexural toughness, flexural strength fatigue resistance, impact resistance, and post-crack strength. The behavior of FRC can be classified in to three groups according to application, fiber volume fraction and fiber effectiveness. Such classification leads to :1) very low volume fraction of fiber (<1%), which has been used for many years now such as age plastic shrinkage control or pavement reinforcement, 2) moderate volume fraction of fiber (1%-2%) for improvement of modulus of rupture (MOR), fracture toughness, impact resistance and other desirable mechanical properties, and 3) high volume fractions of fibers (more than 2%) for special applications such as impact and blast resistance structure.s

The type of fibers which will be used in this study is Steel Fibre. Steel fibers are the most popular material for the reinforced concrete. The performance of the Steel Fiber Reinforced Concrete (SFRC) has shown a significant improvement in flexural strength and overall toughness if compared to plain reinforced concrete.

1.2 Problem Statement

As it is mentioned, concrete is good in compression but weak in tension that is, concrete is a brittle material. So, in order to improve the tensile properties, short fibers are used. Effects of steel fibers on flexural performance of RC beams are what will be investigated in this study.

1.3 Thesis Objectives

The objectives of this study are as follows:

- i. To determine the optimum percentage of steel fibers in SFRC.
- ii. To study the flexural behavior of SFRC beams compared with conventional reinforced concrete beams.
- iii. To study the flexural performance of SFRC beams with lower and higher concrete strength and compared with conventional reinforced concrete beams.

1.4 Scope of study

The scope of study is established to achieve the objectives and this study will be mainly concentrated on experimental works. Experiments regarding to the flexural strength test on the SFRC beams will be carried out in order to study the flexural behavior of the beams. The shape and characteristics of steel fibers which are used in this study are explained in Chapter 3. All testing methods and procedures are specified according to British Standard or American Society Testing Method.

References

ACI Committee 544 (1993). *Guide for Specifying, Proportioning, Mixing, Placing, and Finishing Steel Fiber Reinforced Concrete*, ACI Material Journal, Vol. 90, No.1.

ACI 544.1R (1996). *State-of-the-Art Report on Fiber Reinforced Concrete*, American Concrete Institute, Farmington Hills, Michigan.

Aufmuth, R.E, Naus, D.G , Williamson, G.R. (1974). *Effect of Aggressive Environment on Steel Fibre Reinforced Concrete*, Letter Report M-113.US Army Corps of Engineers. Construction, Engineering Research Laboratory, Champaign, IL.

Barr, B. (1987). *Fracture Characteristics of FRC Materials in Shear*. Fiber Reinforced Concrete Properties and Applications, ACI SP-105, American Concrete Institute, Farmington Hills, Michigan.

British Standard Institution (1983). *Method for Determination of Compressive Strength of Concrete Cubes*. London. BS 1881: Part 116. 73.

British Standard Institution (1992). *Specification for Aggregates from Natural Sources for Concrete*, London, BS 882.

British Standard Institution (1997). *Structural Use of Concrete: Code of Practice for Design and Construction*, London, BS 8110: Part 1.

Chen, Y.Y. and Hwang, C.L. (2001). *Study on Electrical Resistivity and Chloride Ion Penetrability Behavior of Concrete Material*. *Journal of the Chinese Civil and Hydraulic Engineering*.13(2), pp. 293–302 (In Chinese).

Chih-Ta Tsai, Lung-Sheng Li, Chien-Chih Chang,, Chao-Lung Hwang (2009). *Durability Design and Application of Steel Fiber Reinforced Concrete in Taiwan* ,The Arabian Journal for Science and Engineering, Volume 34.

Craig, R.J. (1984). *Structural Applications of Reinforced Steel Fibrous Concrete*. Concrete Int. Design and Construction.

Design of Normal Concrete Mixes, Department of Environment (1988). United Kingdoms.

Fatih Altun , Tefaruk Haktanir, Kamura Ari (2006). *Effects of Steel Fiber Addition on Mechanical Properties of Concrete and RC Beams*. Construction and Building Materials 21, pp. 654–661

Gambhir, M.L. (1995). *Concrete Technology*. (2nd Eddition),.NEW DELHI.Tata McGraw-Hill.

Grzybowski, M. (1989). *Determination of Crack Arresting Properties of Fiber Reinforced Cementitious Composites*. Chapter 12, Royal Institute of Technology, Stockholm, Sweden.

Grzybowski, M. and Shah, S.P. (1990). *Shrinkage Cracking of Fiber Reinforced Concrete*. ACI Materials Journal, Vol. 87, No. 2, pp. 138-148.

Halvorsen, G.T., Kesler,C.E., Robinson,A.R., Stout, J.A. (1976). *Durability and Physical Properties of Steel Fiber Reinforced Concrete*. Report n° DOT-TST 76T-31, US, Department of Transportation, Federal railway administration, Washington DC.

Hannant, D.J. (1978).*Fiber Cements and Fiber Concrete*. John Wiley and Sons Ltd., Chichester, UK, pp 53.

Hartman, T. (1999). *Steel Fiber Reinforced Concrete*. Master Thesis., Department of Structural Engineering. Royal Institute of Technology, Stockholm, Sweden.

Jean-Louis Granju, A. Turatsinze , V. Sabathier and H. Farhat (2005). *Durability of Bonded Cement-Based Overlays: Effect of Metal Fibre Reinforcement*. *Materials and Structures*, Vol.38, No.3.

Johnston, C.D. (1982). *Definition and Measurement of Flexural Toughness Parameters for Fiber Reinforced Concret*. *Cem. Concr. Agg.*

Johnston, C.D, Colin, D. (1982). *Fibre Reinforced Concrete*. *Progress in Concrete Technology CANMET, Energy, Mines and Resources, Canada*, pp 215-236.

Johnston, C.D. (1974). *Steel Fiber Reinforced Mortar and Concrete*. A Review of Mechanical Properties, In fiber reinforced concrete ACI – SP 44 – Detroit.

Kenneth N Derucher, George Korfiatis, Samer Ezeldin (1998). *Materials for Civil & Highway Engineers Book Description*, Prentice Hall

Mangat, P.S. and Gurusmany K. (1985). *Steel Fibre Reinforced Concrete for Marine Applications*. *Proceedings 4th International Conference on Behaviour of Offshore Structures*, Delft, The Netherlands, Elsevier, Amsterdam, pp. 867–879

Mangat, P.S. and Gurusmany, K. (1987). *Permissible Crack Width in Steel Fibre Reinforced Marine Concrete*. *Mat. Struct.* 20, pp. 334–338.

Morse, D.C. and Williamson, G.R. (1977). *Corrosion Behavior of Steel Fibrous Concrete*. Technical report, M-217, US Army Corps of Engineers. Construction Engineering Research Laboratory, Champaign, IL.

Narayanan, R., and Darwish, I. (1987). *Bond Anchorage of Pretensioned FRP Tendon at Force Release*. *ASCE Journal of Structural Engineering*, Vol.118, No.10, pp 2837-2854.

Naaman, A.E. (1985). *Fibre Reinforcement for Concretes*, *Concrete International: Design and Construction*, Vol.7, No.3., pp 21-25.

Neville A.M. (1981). *Properties of Concrete* (Third Edition). Longman Scientific & Technical, pp 642-648.

Noghabai, K. (2000). *Beams of Fibrous Concrete in Shear and Bending: Experiment and Model*. *Journal of Structural Engineering*, ASCE, Vol.126, No.2, pp 243-251.

Ocean concrete products, Ocean Heidelberg Cement Group (1999). *Steel Fibre Reinforcement – Working Together to Build Our Communities Report*.

Oh, S.G., Noguchi T. and Tomosawa, F. (1999). *Evaluation of Rheological Constants of High-Fluidity Concrete by Using the Thickness of Excess Paste*. *Journal of the Society of Materials Science*, August, Japan.

Padmarajaiah, S.K. and Ramaswamy, A. (2002). *Finite Element Assessment of Flexural Strength of Fiber Reinforced High Strength Concrete Prestressed Beams*. *Journal of Cement and Concrete Composites*, Vol.24, No.2, pp.229-241.

Padmarajaiah, S.K., and Ramaswamy, A. (2002). *Comparative Study on Flexural Response of Full and Partial Depth Fiber-Reinforced High-Strength Concrete*. *Journal of Materials in Civil Engineering*, Vol. 14, No. 2, pp. 130–136..

Rapoport, J., Aldea, C., Shah, S.p., Ankenman, B., and Karr, A.F. (2001). *Permeability of Cracked Steel Fiber-Reinforced Concrete*. Technical Report No.115, National Institute of Statistical Sciences (NISS), Research Triangle Park, NC, USA.

Rider, R.G and Heidersbach, R.H. (1980). *Degradation of metal-fiber reinforced concrete exposed to marine environment*. *STP 713, Corrosion of Reinforcing Steel in Concrete*. American Society for Testing and Materials, Philadelphia, pp. 75–92.

Romualdi, J.P. and Baston, G.B. (1963). *Mechanics of crack arrest in concrete with closely spaced reinforcement*, Journal of the Engineering Mechanics Division. EM3, Proceedings of the American Society of Civil Engineers, Vol. 89, pp. 147-168.

Schupack, M. (1985). *Durability of SFRC Exposed to Sever Environments*. Proceedings. Steel Fiber Concrete US-Sweden Joint Seminar (NSF-STU), Swedish Cement and Concrete Research Institute, Stockholm/Sweden, June, pp 479-496.

Schiessl, P. and Weydert R. (1996). *Radical Concrete Technology*. E & FN Spon, Boundary Row, London, pp. 2-6.

Shah, S.P. (1971). *Properties of Fiber Reinforced Concrete*. Journal, ACI, Proceedings, Vol. 68, No. 2, Feb. (with B.V. Rangan)

Snyder, M.J.; Lankard D. R. (1972). *Factors Affecting the Flexural Strength of Steel Fibrous Concrete*. ACI Journal Proceedings, Vol. 69, No. 2, pp. 96-100

Swamy, R.N., Mangat, P.S., and Rao, C.V.S.K. (1974). *The Mechanics of Fiber Reinforcement of Cement Matrices*. An International Symposium: Fiber Reinforced Concrete, Publication SP-44, ACI, pp 1-28

Waterhouse, B.L. and Luke, C.E. (1972). *Steel Fiber Optimization*. Conference Proceedings M-48. Fibrous Concrete-Construction Materials for the Seventies, pp 630-681.

Williamson, G.R. (1978). *Steel Fibers as Reinforcement in Reinforced Concrete*. Proceeding, US Army Science Conference, West Point, Vol.3, pp 363-377.

Williamson, G.R. (1974). *The Effect of Steel Fibers on Compressive Strength of Concrete*, Fiber Reinforced Concrete. SP-44. ACI, pp 195-207, Detroit. Michigan, USA.

Woodrow, T. (1980). *Marine Durability Survey of the Tongue Sands Tower*. Concrete in the Oceans Technical Report No. 5, Taylor Woodrow Research Laboratories, Canada.

Effects of steel fibers on flexural performance of reinforced concrete (RC) beams are the main objectives of this study. The hooked-end steel fibers with the dimensions of 0.75 mm in diameter, 50 mm in length and with the aspect ratio of 67 were used in this study. Initially the optimum percentage addition of steel fibers in concrete was determined. In order to accomplish this task, several concrete prisms and cubes with the same mix proportioning of concrete and different volume fractions of steel fiber (0.5 %, 1%, 1.5 %, and 2 %) were prepared. Then, by determining the flexural and compressi Steel Fiber Reinforced Concrete (SFRC) has gained increased popularity in construction industries in the recent years. Slag is a byproduct of metal smelting and hundreds of tons of it are produced every year all over the world in the process of refining metals and making alloys. Like other industrial by products, slag actually has many uses, and rarely goes to waste.Â 1) The overall flexural behavior of SSRC beams used in this study closely resembles that of equivalent beam made with NWC. 2) The experimental ultimate moment gives a conservative estimate for steel slag concrete beams for 7% to 32% of a theoretical ultimate moment. 9. International Journal of Structural and Civil Engineering.